

# ISO 8217 2010 FUEL STANDARD

## ISO 8217 2010 Fuel Standard for marine residual fuels

### MARINE RESIDUAL FUELS

Limit	Parameter	RMA	RMB	RMD	RME	RMG				RMK		
		10	30	80	180	180	380	500	700	380	500	700
Max.	Viscosity at 50°C (mm <sup>2</sup> /s)	10.00	30.00	80.00	180.0	180.0	380.0	500.0	700.0	380.0	500.0	700.0
Max.	Density at 15°C (kg/m <sup>3</sup> )	920.0	960.0	975.0	991.0	991.0				1010.0		
Max.	Micro Carbon Residue (% m/m)	2.50	10.00	14.00	15.00	18.00				20.00		
Max.	Aluminium + Silicon (mg/kg)	25	40		50	60						
Max.	Sodium (mg/kg)	50	100		50	100						
Max.	Ash (% m/m)	0.040	0.070			0.100				0.150		
Max.	Vanadium (mg/kg)	50	150			350				450		
Max.	CCAI	850	860			870						
Max.	Water (% V/V)	0.30	0.50									
Max.	Pour point (upper) in Summer (°C)	6		30								
Max.	Pour point (upper) in Winter (°C)	0		30								
Min.	Flash point (°C)	60.0										
Max.	Sulphur (% m/m)	Statutory requirements										
Max.	Total Sediment, aged (% m/m)	0.10										
Max.	Acid Number (mgKOH/g)	2.5										
	Used lubricating oils (ULO): Calcium and Zinc; or Calcium and Phosphorus (mg/kg)	The fuel shall be free from ULO, and shall be considered to contain ULO when either one of the following conditions is met: Calcium > 30 and zinc > 15; or Calcium > 30 and phosphorus > 15.										
Max.	Hydrogen sulphide (mg/kg)	2.00										

The above is a service for informational purposes only. Dan-Bunkering assumes no responsibility for any errors or omissions.